

## Product Information (PI) Sheet

**Product:** Vinyl Lacquer Sealer

**Code(s) :** C101 83

**Description:** A modern vinyl modified nitrocellulose lacquer sealer with a unique non-stearated sanding aid. It is formulated to offer an improvement over conventional lacquer sealers where excellent adhesion, stain blocking and superior moisture resistance is required.

**Uses:** Vinyl Lacquer Sealer is recommended for job finishing of kitchen cabinets or institutional furniture where extra moisture resistance is needed. For better adhesion and film properties, this sealer contains no stearate type sanding aid. Use a "Fre-Cut" (no fill) type sand paper. Only scuff sanding is recommended with this sealer. Can also be used as a sealer under pre-catalyzed lacquer.

**Other Products:** For conventional lacquer sealers having good flow and sanding, see M.L. Campbell Easy Sanding Sealer. See also M.L. Campbell WoodSong II Stains.

Physical Properties (packaged)	
<b>Weight per Gallon:</b>	7.52 lbs. ± .1lbs
<b>Viscosity - Ford #4 at 77°F/25°C:</b>	18 - 22 seconds
<b>% Solids - by Weight:</b>	19 - 22
<b>% Solids - by Volume:</b>	13 - 17
<b>Theoretical Coverage at 1 Mil Dry:</b> (Coverage figures DO NOT INCLUDE spray loss. Also allow for surface irregularities and porosity of wood surface to be finished.)	247 sq. ft. per gallon
<b>Flash Point (PMCC):</b>	37°F or 7°C
<b>Color:</b>	Cloudy
<b>Packaged VOC:</b>	719 g/l (6.0 lbs/gallon)
<b>Photochemically Reactive:</b>	Yes

Surface Preparation	
<b>New Work:</b>	Remove any dirt, grease, glue or other construction contaminants and sand wood as required. Apply stain, if specified, as directed prior to finishing.
<b>Old Work:</b>	Strip old finishes completely and remove all contaminants from the surface. Make sure surface is dry, sand as required. Finish as new work. If cratering develops on work, Fish Eye Killer WR5 may remedy this problem (if the contaminant is not too severe). <b>Note:</b> The use of excessive film build of any sealer will cause deterioration of the adhesion and mar-resistance of the total finishing system. The use of a sealer in any finishing system should be limited to one or two coats.

Reduction	
No reduction is required; however, small amounts of lacquer thinner (C16036 Standard Lacquer Thinner) may be used if required for specific equipment. No more than 10–15% is recommended.	

## Application Procedure

**Refer to spray equipment suppliers for recommendations on fine atomizing spray guns, air caps and fluid needles. Note: Hot Spray application is not recommended.** If hot spray equipment is used, temperature setting should never be over 110° F or 43° C.

## Equipment Clean Up

- Use lacquer thinner to clean up all equipment.
- Dispose of dirty solvent and cleaning rags in a safe and approved manner.
- Solvent or lacquer-soaked rags should be stored in water-filled, closed containers prior to disposal.

## Drying Times (at 77°F or 25°C)

<b>Dry to Touch:</b>	15 Minutes
<b>Sanding Dry:</b>	25 Minutes
<b>Stacking Dry:</b>	12 – 24 hours

## Packaging/Shipping

**Available Units:** Gallons and Pails.

## Shelf Life and Storage

- Package life is (3) three years - Store in a cool dry area in the original sealed containers.
- Do not store around any source of flames or sparks.
- Spills should be cleaned up with non-sparking tools and inert absorbent material.
- If stored at temperatures below 30°F (0°C), this product may gel. If so, warming to room temperature will restore it to usable condition.

## DOT Classification

Flammable Liquid	Red Label	UN 1263
------------------	-----------	---------

## B/L Description

Paint	UN 1263	3	PG II
-------	---------	---	-------

## Caution

- **THESE PRODUCTS ARE DESIGNED FOR SHOP APPLICATION AND PROFESSIONAL USE ONLY.**
- Use only after all safety information is understood.
- Refer to the Material Safety Data Sheet (MSDS) for additional information.

## Testing

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, customers should test the complete system for adhesion and compatibility under their conditions prior to full-scale application.

## Notes

The information, rating, and options stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application that are not known or under our control, M.L. Campbell cannot make any warranties as to the end result. *Thank you for using M.L. Campbell Wood Finishing products.*